



ALPERTON Engineering Ltd.

Moyle Road, Dublin Industrial Estate, Glasnevin, Dublin11, Ireland

Phone +353 1 8306277 : Fax +353 1 8306458 : info@alperton.ie : www.alperton.com

Material Specification 105

(Typical Properties)

Product: 25% Glass Fibre Filled PTFE (polytetrafluoroethylene)

Property	Method	Units	Specification
Specific gravity	ASTM D792	g/cc	2,230 – 2,260
Tensile strength	ASTM D4894	MPa	13 – 18
Elongation	ASTM D4894	%	180 - 220
Hardness	ASTM D2240	Shore D	60 - 65
Deformation under load (140 Kg/cm ² for 24 hrs. At 23°C)	ASTM D695	%	10 - 12
Permanent deformation (after 24 hrs. Relaxation at 23°C)	ASTM D695	%	5 – 6
Friction Coefficient	ASTM D1894	/	0,15 (Dynamic)
Volume Resistivity	ASTM D257	Ohm cm	10 ¹⁵
Water Absorbtion	ASTM D570	%	0.013
Service Temperature		C°	-200 / +260
Excellent resistance to continuous service temperature up to 260°C and, for limited periods, even to higher temperatures, the low temperature resistance of the product allows satisfactory performance at -200°C			
Flamability	UL 94	%	V-0
Melting Point		C°	325 – 335

FDA Approved:

(Code of Federal regulation 21 CFR Ch.1, revised as of April 1, 1999 Edition);
Sections 175.105-175.300-176.170-176.180-177.1520-177.1550-177.2600-178.3570.
"Perfluorocarbon Resins" of the Food and Drug Administration/USA.

All information supplied by or on behalf of Alperton Engineering Ltd in relation to its products, whether in the nature of data recommendations or otherwise is supported by research and believed reliable but Alperton Engineering Ltd assumes no liability whatsoever in respect of application processing or use made of the aforementioned information or products or any consequence thereof. The buyer undertakes all liability in respect of the application processing or use of the aforementioned information or product, whose quality and other properties he shall verify or any consequence thereof. No liability whatsoever shall attach to Alperton Engineering Ltd for any infringement of the rights owned or controlled by a third party intellectual industrial or other property by reason of the application processing or use of the aforementioned information or products by the buyer.