

# Static Control Pomalux®

(static control acetal)

**Pomalux SD-A (Static-dissipative acetal copolymer)** Non-carbon-filled, permanently static-dissipative material which is non-migratory and non-humidity dependent. With enhanced lubricity, Pomalux SD-A provides superior wear resistance and ease of machining. Its extremely low outgassing values and non-sloughing characteristics make it ideal for applications where particulate generation cannot be tolerated. Enhanced lubricity, chemically resistant, and dimensionally stable.

**Pomalux CN-F (Conductive Acetal Copolymer)** Non-sloughing carbon-fiber-filled material which is extremely strong and stiff with excellent dimensional stability. Abrasion-resistant, highly chemical-resistant, with temperature resistance to 320° F.

**Pomalux CN-SS (Conductive Acetal Copolymer)** Stainless-steel-fiber-filled, non-sloughing, dimensionally stable material HDT @ 264 psi of 225° F. This material has relatively high chemical resistance, is extremely strong and stiff, and is an excellent choice for situations where carbon-based conductive fillers are not acceptable. Easily machined with carbide-tipped tooling to tight tolerances.

The following physical property information is based on typical values of the resin.

	Units	ASTM Test	Pomalux SD-A	Pomalux CN-F	Pomalux CN-SS
<b>Mechanical</b>					
Tensile strength @yield	psi	D638	6,600	11,900	8,600
Tensile elongation @break	%	D638	45.0	3.5	-
Flexural strength	psi	D790	7,000	14,300	13,000
Flexural modulus	psi	D790	210,000	1,225,000	400,000
Izod impact strength					
Notched	ft•lbs/in	D256	2.0	1.0	0.7
Un-Notched	ft•lbs/in	D256	no break	3.5	-
Hardness-Shore D		D2240	76	88	86
<b>Thermal</b>					
Heat deflection temperature					
@264 psi	°F	D648	141	320	225
@66 psi	°F	D648	267	-	-
Coefficient of thermal expansion	in/in/°F	D696	6.5 x 10 <sup>-5</sup>	-	4.9 x 10 <sup>-5</sup>
Thermal conductivity	(BTU•in)/(hr•ft <sup>2</sup> •°F)		2.10	-	-
Flammability rating-UL94			HB	HB	-
<b>Electrical</b>					
Surface resistivity dry	ohm/sq	D257	10 <sup>9</sup> - 10 <sup>11</sup>	10 <sup>2</sup> - 10 <sup>6</sup>	10 <sup>2</sup> - 10 <sup>6</sup>
Volume resistivity dry	ohm/cm	D257	10 <sup>9</sup> - 10 <sup>11</sup>	10 <sup>3</sup> - 10 <sup>7</sup>	10 <sup>2</sup> - 10 <sup>6</sup>
Static decay, 15% RH	seconds	MIL-B-81705-B	<0.3	<0.1	-
<b>Other</b>					
Specific gravity		D792	1.33	1.46	1.5
Water absorption @24 hours	%	D570	2.50	0.22	-

CN-F = conductive carbon-fiber-filled material  
 SD-A = static-dissipative non-carbon-alloy-filled material  
 CN-SS = conductive stainless-steel-fiber-filled material

<sup>1</sup>Ultimate elongation



**Alperton Engineering Ltd**


Dublin Industrial Estate,  
 Glasnevin, Dublin 11, Ireland.

www.alperton.com info@alperton.ie  
 Phone +353 1 8306277 Fax +353 18306458

**WESTLAKE  
 PLASTICS COMPANY**

**World Headquarters**  
 P.O. Box 127, Lenni, PA 19052  
 1-800-999-1700 • Fax: (610) 459-1084

www.westlakeplastics.com



**Applications Include:**

- Disk drive assembly fixtures
- Semiconductor/electronic components
- Telecommunication hardware
- Automotive equipment

**Advantages of Pomalux SD-A, CN-F and CN-SS:**

- Low outgassing
- Consistent resistivity values
- Ease of machining
- Good chemical resistance

**Manufacturing Capabilities:**

- Rod:** 1/8" to 4" diameter
- Sheet**(CN-F & CN-SS): 1/4" to 4" thick
- Sheet**(SD-A): .030" to 4" thick
- Film**(SD-A only): .010" to .029" thick

**Colors/Grades:**

- SD-A—Natural (beige)
- CN-F—Black
- CN-SS—Dark Gray

\*In addition to our standard capabilities, Westlake also has the ability to process custom resins in various sizes and colors with some exceptions.

**West Coast Office**  
 377 E. Chapman Ave., Suite 120, Placentia, CA 92870  
 1-800-440-0597 • Fax: (714) 961-0978

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe

any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.

Pomalux® is a Registered Trademark of Westlake Plastics Co.