

Technical Data
TIVAR® Materials

TIVAR®
Burnguard

Material designation

ISO designation	PE-UHMW
Material description	Ultra High Molecular Weight Polyethylene, flame retardent properties

Colour(s)	black
-----------	--------------

Material properties	Standard	Unit	
----------------------------	-----------------	-------------	--

Average molecular weight (average molecular mass)		(g/mol)	approx. 5×10^6
Density	ISO 1183	(kg/m ³)	1000 - 1050
Water absorption at 23° C until saturation	ISO 62	(%)	< 0,01

Mechanical properties	Standard	Unit	
------------------------------	-----------------	-------------	--

Tensile stress at yield (tensile strength)	ISO 527	(MPa)	≥ 17
Elongation at break	ISO 527	(%)	≥ 150
Tensile modulus	ISO 527	(MPa)	700
Impact strength (Charpy) at 23° C	ISO 179	(kJ/m ²)	no break
Notched impact strength (Charpy) at 23° C	ISO 11542-2	(kJ/m ²)	80
Ball indentation hardness	ISO 2039-1	(N/mm ²)	30 - 35
Shore-Hardness D, 15 s value	ISO 868	(-)	60 - 65
Coefficient of friction	-	(-)	approx. 0,25
Abrasion (Sand-Slurry)	-	(%)	130

Thermal properties	Standard	Unit	
---------------------------	-----------------	-------------	--

Melting point DSC, 10 K/min	ISO 3146	(°C)	135 - 138
Vicat softening point	ISO 306	(°C)	80
Coefficient of linear thermal expansion between 23 and 80° C	ISO 11359	(K ⁻¹)	approx. 2×10^{-4}
Thermal conductivity	ISO 52612	(W/[m * K])	approx. 0,4
Use temperature (max.)	-	(°C)	80
Use temperature (briefly)	-	(°C)	90
Use temperature (min.)	-	(°C)	-200

Electrical properties	Standard	Unit	
------------------------------	-----------------	-------------	--

Relative permittivity at 100 Hz	IEC 60250	(-)	-
Dissipation factor at 100 Hz	IEC 60250	(-)	-
Volume resistivity	IEC 60093	(Ohm * m)	< 10^2
Surface resistivity	IEC 60093	(Ohm)	< 10^3
Dielectric strength	IEC 60243	(kV/mm)	-

Physiological properties	Standard	Unit	
---------------------------------	-----------------	-------------	--

Food conformances according to EU Directive 2002/72/EC			no
FDA Regulation 21CFR177.1520			no
FDA Regulation 21CFR178.2010			no
FDA Regulation 21CFR178.3297			no

Ratings	Standard	Unit	
----------------	-----------------	-------------	--

UL 94		Thickness ≥ 6 mm	V-0
DIN 5510-2		Thickness ≥ 10 mm	Class S4 smoke classification SR 2 dripping classification ST2
FMVSS 302		Thickness ≥ 15 mm	not inflammable
BS 476, Part 7		Thickness ≥ 6 mm	Class 2

Notice to users:

The technical data shown in this data sheet refers to a 40 mm thick sheet. Due to the production process the data may vary depending on the material thickness.

The information contained in this technical data sheet can not be construed as a promise or guarantee of specific properties of our products. Any determination of the suitability of a particular material and part design for any use contemplated by the user is the sole responsibility of the user. The information contained in this technical data sheet is based on present knowledge and may be subject to change without further notice.

Issue August 2006